

Odorless Bright Red Auto Paint Multipurpose Alkali Resistant

Our Product Introduction

for more products please visit us on refinishcarpaint.com

Basic Information

- Place of Origin: China
- Brand Name: Faralli
- Certification: ISO,MSDS,SGS
- Model Number: 217
- Minimum Order Quantity: 100 L
- Price: 3.26USD-5USD
- Packaging Details: 1L*12tins, 4L*6tins, 4L*4tins, 0.5L*24tins, 10L, 20L, 200L
- Delivery Time: 5-8days
- Payment Terms: T/T
- Supply Ability: 500000L/month



Product Specification

- Application Method: Brush, Roller, Or Spray
- Coverage: 400 Sq. Ft. Per Gallon
- Product Name: Car Paint Topcoat
- VOC Level: Low
- Color: Color Chart And Customized
- Cleanup: Soap And Water
- Fade Resistance: Yes
- Solvent Resistance: Yes
- Coating Thickness: 3-4 Mills
- Feature: Long Lasting, Moisture Resistant, Easy To Clean, Fast Dry, Smooth
- Highlight: **auto body paint matching, paint restoration for cars, 1k paint**



More Images



Product Description

2K Bright Red Auto Paint | Fast Drying Time & High Gloss Coverage Automotive Acrylic

Product Description

This high-quality 2K acrylic paint is designed for mid to high-end cars, boasting excellent weather resistance, high gloss, good hardness, high film thickness, and strong adhesion, making it ideal for partial spraying of new cars or repairing old ones.

Products Catalogue	Package Size	Mxing Ratio(by Volum)	Dry to Handle	Quality assurance time
Primer	1L*12&3.75L*4	100:25:25	90-120 minutes	4 years
1K Base coat	1L*12&3.75L*4	100:(10-20)	5 minutes	4 years
2K Solid color	1L*12&3.75L*4	100:50:(20-30)	24 hours	4 years
Clear coat	5L*4/4L*6/1L*12	100:50:(10-20)	90-120 minutes	4 years

2K Automotive Paint Construction Process

Type	2K car paints and refinishes				
Substrates	Well-Sanded, Completely dried and good existing finishes as below: A. Original paint B. Old paint firm C. 1K or 2K primer				
Mixing Ratio	2K Solid Colors(2)	Hardener(1)	Thinner(0.2-0.4)		
<15°C	2K Solid Colors	120 Fast Hardener	602 Fast Thinner		
15-30°C	2K Solid Colors	120 Standard Hardener	602 Standard Thinner		
>30°C	2K Solid Colors	120 Slow Hardener	602 Slow Thinner		
Spray Viscosity	16-19s to drop off, in 4# viscosity cup at 25°C				
Re-Treatment	There are particles or runs after spray, sand affected area with P2000 sand paper after thorough dring, then polish to solve it.				
Spray Gun Set Up	Gravity Feed: 1.2-1.5mm 3-5kg/cm ² Gravity Feed: 1.4-1.6mm 3-5kg/cm ²				
Spray Technology	Coats & Thickness: 2-3 coats, total 35-50um Flash-Off Time: At 25°C ,5-10 minutes between two coats Air-Drying Time: Allow 10-15 minutes air drying before force drying				
Drying Time	Temperature	Dust Free	Tack Free	Dry to Handle	Dry to Test
	25°C	40minutes	2 hours	9 hours	6 days
	70°C	5 minutes	10 minutes	25 minutes	50minutes
OEM ODM	As customers' order				
Shelf Life	2 years in original sealed can, cool and dry place at 25°C				
Package Size	1L*12 Tins or 3.75L*4 Tins				

The 2K Top Coat is a high-quality acrylic paint designed for mid to high-end cars. It offers a range of characteristics that make it an excellent choice for automotive applications, including high gloss, excellent weather resistance, high film thickness, good hardness, and good adhesion. The top coat is suitable for use in both partial spraying of new cars and repairing old cars. Its high-quality formulation ensures a long-lasting finish that is resistant to weather and other external elements. Overall, the 2K Top Coat is a reliable and durable choice for automotive painting that offers excellent gloss and weather-resistant properties.

Advantages:

1. Excellent protective and covering power with long lasting bright color.
2. Outstanding mechanical and chemical resistance.
3. Tough and durable film provide strong anti-UV Stability and gloss retention
4. Splendid and durable color performance.

Physical properties

Product Name	2K top coat
Density	0.92-1.25 kg/L
Raw materials	Acrylic Resin, Additive, Solvent, Polyurethane resin
Colors	multiple colour. See the product list below for details.
Solid content	50%

Notes:

Clear coat should not be sprayed over light-colored paint to prevent the color from turning yellow.
Use 800# fineness sandpaper to sand the primer before spraying the topcoat.
Ensure that the primer has thoroughly dried before spraying the topcoat to avoid blisters.





2K
217



Bright Red

Product Features

- The front is slightly blue, the side is yellow, and the vividness is high



Guangzhou Meklon Chemical Technology Co., Ltd.



+8613392100968



Meklonpaint@gzmeklon.com



refinishcarpaint.com

Room 1309, Tower B, Jiada International, Guangyun Road, Baiyun District, Guangzhou City, Guangdong Province