



Basic Information

Place of Origin: ChinaBrand Name: Faralli

• Certification: ISO,MSDS,SGS

Model Number: 220Minimum Order Quantity: 100 L

• Price: 3.26USD-5USD

Packaging Details: 1L*12tins, 4L*6tins, 4L*4tins, 0.5L*24tins, 10L, 20L, 200L

Delivery Time: 5-8daysPayment Terms: T/T

Supply Ability: 500000L/month



Product Specification

Application Method: Brush, Roller, Or Spray
 Coverage: 400 Sq. Ft. Per Gallon
 Product Name: Car Paint Topcoat

• VOC Level: Low

Color: Color Chart And Customized

• Cleanup: Soap And Water

Fade Resistance: Yes
Solvent Resistance: Yes
Coating Thickness: 3-4 Mils
Usage: Car Paint
Application Method: Spray, Brush

Highlight: Rose Red Car Paint Top Coat, car color repair,

one stage paint



More Images



Product Description

2K Rose Red Car Paint Top Coat | Fast Hardener, Standard & Slow Thinner Mixing

Product Description

Characteristic:Faralli 2K Solid Colors, high gloss and build, good performance of leveling property, easy construction, excellent pretective and coveraging power, long lasting bright color. Mainly applies to intermediate cars, MPV and bus.

2K Rose Red is a high performance paint commonly used in the painting of cars and other vehicles. The following are the properties and benefits of 2K Rose Red:

Vibrant Color: 2K rose red has a bright and vibrant color, which can add vibrant color to the vehicle and improve the visual appeal of the vehicle.

High brightness: 2K rose red has high brightness, which can improve the glossiness of the vehicle surface, making it look more smooth and textured.

Strong Weather Resistance: The 2K rose red is made of high-quality materials with excellent weather resistance, which can maintain a good appearance and color stability even in harsh climate conditions.

Strong wear resistance: The 2K rose red coating is very hard and wear-resistant, which can effectively protect the vehicle surface from scratches, abrasions and other damages.

Ease of application: 2K rose red is easy to apply, can be applied by spraying or brushing, etc., and has the characteristics of quick drying, which makes the application process more efficient.

2K Automotive Paint Construction Process

	Well-Sanded, Completely dried and good existing finishes as bellow:				
Substrates	A original paint B. Old paint firm C. 1K or 2k primer				
Surface Cleaning	Wash by warm soap, remove wax, silicon and other contaminations with degreaser, sanding with P800-P1000, wash with clean water then keep dry; again with degreaser.				
Mixing Ratio	Faralli 2K Solid	ralli 2K Solid Colors Hardener			Thinner
	2		1		0.2-0.4
15	Faralli 2K Solid	Colors	MS120 Fast Hardener		602 Fast Thinner
15-30	Faralli 2K Solid	Colors	MS120 Standard Hardener		602 Standard Thinner
30	Faralli 2K Solid	Colors	MS120 Slow Hardener		602 Slow Thinner
Spray Viscosity	16-19s to drop off, in 4# viscosity cup, at 25°C,				
Pot-life	At 25°C 2 hours with fast hardener. 4 hours with standard or slow hardener.				
ReTreatment	There are particles or runs after spray, sand affected area with P2000 sand paper after thorough drying, then polish to solve the problem.				
Spray Gun Set	Gravity Feed: 1.2-1.5mm 3-5kg/cm 2				
Up	Suction Feed: 1.4-1.6mm 3-5kg/cm 2				
Spray Technology	Coats&Thickness: 2-3 coats, total 35-50um Flash-Off Time: At 25°C, 5-10 minutes between two coats, Air-Drying Time: Allow 10-15 minutes air drying time before force drying				
Drying Time	Temperature	Dust Free	Tack Free	Dry To Handle	Dry To Test
	+25°C	40 minutes	2 hours	9 hours	6 Days
	+70°C	5 minutes	10 minutes	25 minutes	50 Minutes
Shelf Life	2 years in original sealed can, cool and dry place at 25.				
Package	1L×12 or 3.75L×4				

Note:

- 1. The substrate must be cleaned and sanded before spray, wet sanding P800-1000 and then dry.
- 2. At ambient temperature higher than 30, add appropriate Retarder Solvent into thinner to avoid blushing. For more details, please refer to technical data sheet of Retarder Solvent.
- 3. The products mixed with hardener should be used up soon and can not be restore for future use; clean equipments immediately with thinner after application, otherwise it is very difficult to be cleaned after dry.

















Guangzhou Meklon Chemical Technology Co., Ltd.



+8613392100968



Meklonpaint@gzmeklon.com



refinishcarpaint.com

Room 1309, Tower B, Jiada International, Guangyun Road, Baiyun District, Guangzhou City, Guangdong Province