

**GUANGDONG CHINA** 

Ferrari series

X-03

ISO,SGS,MSDS

3.26USD-5USD

7-30days

50000L/month

T/T

0.5L/1L/4L/10L/20L/200L

# HS 1K Crystal Bronze Auto Paint: High Application & Raw Materials for Car Body

# **Basic Information**

- Place of Origin:
- Brand Name:
- Certification:
- Model Number:
- Minimum Order Quantity: 100 L
- Price:

Our Product Introduction

- Packaging Details:
- Delivery Time:
- Payment Terms:
- Supply Ability:



# **Product Specification**

- Main Raw Materials:
- Feature:
- Color:
- Substrate:
- Shelf Time:
- Component Style:
- High Light:
- Coating Type:
- Highlight:

# Acrylic Resin,Polyurethane Resin High Leveling,high Glossy,high Fullness,good Covering,high Adhesion Transparent,transparent With Light Yellow 1k Base Coat 2 Years,at 20 Bi-component Anti Scratch Auto Base Paint, Oil Based Auto

- Anti Scratch Auto Base Paint, Oil Based Au Base Paint, Acrylic Car Primer High Adhesion
- Acrylic
  - 1K Crystal Bronze Auto Paint





## More Images



## HS 1K Crystal Bronze Auto Paint: High Application & Raw Materials for Car Body

### **Product Description**

Extra fast drying and high quality finish. Superior inter-coat adhension and reduces the possibility of mottling or unevenness in the finish. Good covering power and leveling. Complete color coverage range with outstanding color accuracy.

### Our full product ranges include the following:

- 1.Car Paint 2K Topcoat solid colors
- 2.Car Paint 1K basecoat metallic colors
- 3. Auto Paint 2K high solid and standard clear coat
- 4.Auto putty
- 5. Automotive 2K primers and 1K primer
- 6. Automotive Paint Binders and fixatives
- 7. Automotive Paint Related hardener, thinner and other solvent

Crystal Copper Pearl is a high-grade automotive coating with the following properties and characteristics:

Leveling property: crystal copper pearl paint has excellent leveling property, which can form a flat, smooth and blemish-free surface during the construction process, so that the surface of the car body presents an excellent touch and texture. Gloss: The surface gloss of crystal copper pearl paint is very high, which can reflect dazzling light, so that the surface of the car body presents a unique pearl luster, which increases the visual effect of the vehicle.

Bright colors: The crystal copper pearl paint is bright and bright, with good color saturation, which can attract people's attention and improve the visual effect of vehicles.

Weather resistance: Crystal copper pearl paint has excellent weather resistance, can resist the erosion of ultraviolet rays, oxidation, acid rain and other harsh environments, and maintain a long-term aesthetic effect.

Easy construction: The construction process of crystal copper pearl paint is simple and easy to use, and the coating can be completed in a short time to improve work efficiency.

Effect of raw materials: The raw materials of crystal copper pearl paint are mainly mixed with high-quality pigments and pearl powder. These raw materials can effectively improve the color brilliance and pearl luster of the paint.

In conclusion, Crystal Copper Pearl Paint is a high-grade automotive paint with unique properties and characteristics. It has excellent leveling and gloss, and can form a flat, smooth, blemish-free surface, giving the car body surface an excellent touch and texture. At the same time, the color of crystal copper pearl paint is bright and bright, with good color saturation, which can attract people's attention. In addition, crystal copper pearl paint has excellent weather resistance, easy construction, and excellent raw material effects, and is a very popular high-end automotive paint.

|                     | Well-Sanded, Completely dried and good existing finishes as bellow:<br>A original paint B. Old paint firm C. 1K or 2k primer |                     |
|---------------------|--|---------------------|
| Surface Cle         | Wash by warm soap, remove wax, silicon and other contaminations with degreaser, sandingwith P800-P1000,                      |                     |
| aning               | wash with clean water then keep dry;again with degreaser.  |                     |
| Mixing Rati         | 1K Crystal Bronze Pearl Colors X-03, Car Basecoat Colors   | Thinner             |
| C                   | 1  | 1                   |
| 15                  | 1K Crystal Bronze Pearl Colors X-03  | 602 Fast Thinner    |
| 15-30               | 1K Crystal Bronze Pearl Colors X-03  | 602 StandardThinner |
| 30                  | 1K Crystal Bronze Pearl Colors X-03  | 602 Slow Thinner    |
| Spray Visco<br>sity | 14-16s to drop off, in 4# viscositycup at 25°C,  |                     |
| ReTreatme<br>nt     | After spray, allow 10-20 minutesair-drying time, then spray clear coat at once.  |                     |
| Spray               | Gravity Feed: 1.2-1.5mm 3-5kg/cm 2   |                     |
| Gun Set Up          | Suction Feed: 1.4-1.6mm 3-5kg/cm 2   |                     |
| Spray Tech          | Coats&Thickness: 2-3 coats, total 15-20um.   |                     |
| nology              | Flash-Off Time: At 25°C, 5-10 minutes between two coats, it depends on temperature and paint film.                           |                     |
| Shelf Life          | 2 years in original sealed can, cool and dry place at 25 .   |                     |
| Package             | 1L×12 or 3.75L×4   |                     |
| Note:               |  |                     |

1. The substrate must be cleaned and sanded before spray, wet sanding P800-1000 and then dry.

2. At ambient temperature higher than 30, add appropriate Retarder Solvent into thinner to avoid blushing. For more details, please refer to technical data sheet of Retarder Solvent.

3. To avolid problems of mottling or poor adhesion, the metallic paint film should be 15-25um.













